



VeroWhite FullCure[®]830 – Data Sheet

Property	ASTM Standard	Value (Metric)	Value (Imperial)
Tensile Strength	D-638-03	49.8 Mpa	7221 psi
Modulus of Elasticity	D-638-04	2495 Mpa	361,775 psi
Elongation at break	D-638-05	20 %	20 %
Flexural Strength	D-790-03	74.6 Mpa	10817 psi
Flexural Modulus	D-790-04	2137 Mpa	309,865 psi
Izod Notched Impact	D-256-06	24.1 J/m	0.45 ft lb/in
HDT 0.45 MPa	D-648-06	43 °C	109 °F
Tg	DMA, E"	58 °C	136 °F